

B5004



High Density Polyethylene

Blow Molding

Product Description:

HDPE B5004 is a natural colored grade produced with the latest Mitsui CX slurry polymerization

Technology exhibiting following features:

- ✓ Good Processing Properties
- ✓ Excellent ESCR Properties
- ✓ Good external appearance

HDPE B5004 is recommended for following applications:

- ✓ Bottles & containers up to 10 L
- ✓ Packaging of Pesticides & Surfactants
- ✓ Bottles for Shampoo and Cosmetics

Typical Properties:

Sr. No.	Properties	Test Method	Units	Values*
Physical Properties				
1	Melt Flow Index (190°C & 2.16 kg)	ASTM D1238	g / 10 min	0.40
2	Density (at 23 °C)	ASTM D1505	gm/cm ³	0.950
Mechanical Properties				
3	Tensile Strength @ Yield (50mm / min)	ASTM D638	MPa	24
4	Tensile Strength @ Break	ASTM D638	MPa	>15
5	Elongation @ Break (50mm / min)	ASTM D638	%	>500
6	Notched Izod Impact Strength (at 23 °C)	ASTM D256A	J/m	140
7	Charpy Impact Strength	ISO 179-1	KJ/m ²	8.5
8	Flexural Modulus	ASTM D790A	MPa	900
9	ESCR (F ₅₀ , 10% Igepal Soln. v/v)	ASTM D1693B	Hours	>500
10	Hardness	ASTM D2240	Shore D	65
Thermal Properties				
11	Vicat Softening Point (10N)	ASTM D1525	°C	121
12	Heat Deflection Temperature (0.455 Mpa)	ASTM D648	°C	78
* Mechanical Properties tested on Compression Molded Specimen.				
* Typical Values and not to be taken as specification limits, values may change without any prior notice.				

Recommended Processing Temperature: 160 – 200 °C

Disclaimer: OPaL assumes no liability whatsoever in respect of application, processing or any use made of the afore - mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore - mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attached to any of the OPaL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of application, processing or use of the afore-mentioned information or products by the user.

B5004



Regulatory Requirements:

HDPE Blow Molding grade B5004 shall meet the requirements stipulated in IS 10146:1982 on 'Specification of Polyethylene for safe use in contact with Foodstuff, Pharmaceutical & Drinking water'. The grade and Additives incorporated in this grade shall meet the positive list of constituents as prescribed in IS 10141:1982. The Grade and the additives incorporated in it shall also comply with the FDA: CFR Title 21,177.1520, Olefin Polymers.

Storage & Handling:

Prevent Polyethylene Material from direct exposure to sunlight & heat to avoid quality deterioration. The storage location should be dry, dust free and the Storage temperature should not exceed 50 °C. Non - compliance to these precautionary measures can lead to degradation of the product causing Color changes, Odor & inadequate product performance.

Health and Safety Information:

The product described herein may require precautions in handling and use because of toxicity, flammability, or other consideration. The Material Safety Data Sheet (MSDS) contains the available product health and safety information for this material and can be found at www.opalindia.in. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.



ONGC Petro additions Ltd

Disclaimer: OPaL assumes no liability whatsoever in respect of application, processing or any use made of the afore - mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore - mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attached to any of the OPaL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of application, processing or use of the afore-mentioned information or products by the user.

Contact: ONGC Petro Additions Ltd., Polymer Marketing Group: 1st Floor, Omkara Complex, Sai Chowkdi, Manjalpur, Vadodara 390011, Gujarat,India
Telephone: +91 265 6192600, Fax: +91 265 6192666, Corporate Site: www.opalindia.in PARC/2016/03 - 00