

Sipchem LD 2023

Low Density Polyethylene Resin

Product description: Sipchem LD 2023 Low Density Polyethylene resin, manufactured by IPC[†] in The Kingdom of Saudi Arabia using an Exxon-Mobil high-pressure tubular process.

LD 2023 is designed to offer a good balance of optical and mechanical properties.

Applications: Blend Partner, Cast Film, Compounding, Foam, Food Packaging, Form Fill and Seal Packaging, Freezer Film, Lamination Film, Light Duty Shrink Film, Liners, Mail Bag, Produce Bags, Shoppers, Textile Packaging, Tough Medium Sized Molding

Properties	Typical Value ¹	Unit	Test Method
Melt Index (190°C / 2.16 kg)	2.0	g/10 min	ASTM D1238
Density	0.923	g/cm ³	IPC Method
Melting Point	110	°C	ASTM D3418
Tensile Strength at Yield MD	11	MPa	ASTM D882
Tensile Strength at Yield TD	11	MPa	ASTM D882
Tensile Strength at Break MD	25	MPa	ASTM D882
Tensile Strength at Break TD	22	MPa	ASTM D882
Elongation at Break MD	330	%	ASTM D882
Elongation at Break TD	550	%	ASTM D882
Secant Modulus MD – 1% Secant	210	MPa	ASTM D882
Secant Modulus TD – 1% Secant	230	MPa	ASTM D882
Drop Dart Impact	80	g	ASTM D1709A
Elmendorf Tear Strength MD	150	g	ASTM D1922
Elmendorf Tear Strength TD	120	g	ASTM D1922
Gloss (45°C)	63	g	ASTM D2457
Haze	6.1	%	ASTM D1003

1. These are typical properties: these are not to be construed as specifications.
2. This product is not intended for use in medical applications and should not be used in any such applications.
3. Contact your Sipchem Representative for potential food contact application compliance.

[†]IPC [International Polymers Company]
PO Box 12021
Jubail Industrial City - 31961
Kingdom Of Saudi Arabia

IPC is an affiliate of Sipchem

October 2013 – v 3.6
Page 1/1

+966 3 801 9255

The preliminary information in this document is provided for pre-marketing purposes only, and relates only to the named product or materials when not in combination with any other product or materials. The information and recommendations presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made. Before using one of the products mentioned herein, customers and other users should take care in determining the suitability of such product for the intended use. Sipchem and International Polymers Company therefore, do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein.